



DATA SHEET

Filter media

Blended 80/20

Blended 80/20

| | |
|---|---|
| Appearance | White, corrugated |
| Use | Pleatable filter media |
| Composition | Blended Cellulose + Synthetic |
| Area weight | 130 g/m ² |
| Thickness | 0.35 mm |
| Air Permeability (Frazier) | 540 m ³ /m ² .h at 125 Pa |
| IFA/BIA certificate (DIN 660335-2-69) | Class M Test report number: 201723219/6120 |
| Temperature (dry heat) | |
| Continuous | 65 °C |
| Peaks | 80 °C |
| Chemical resistance | |
| Hydrolysis | N/A |
| Acids | Poor |
| Alkalis | Fair |
| Oxidising agents | Poor |
| Organic solvents | Fair |
| Abrasion resistance | Good |
| Supports combustion | Yes |
| Application field | Fine dust fumes caused by laser and plasma cutting, welding fumes, shot blasting. |