



DATA SHEET

Filter media
Polyester Anti-Static

Polyester Anti-Static

| | |
|---|---|
| Treatment | Conductive / Anti-Static |
| Use | Pleatable filter media |
| Composition | 100% Polyester |
| Area weight | 250 g/m ² |
| Thickness | 0.56 mm |
| Air Permeability | 510 m ³ /m ² /h at 200 Pa |
| Surface electrical resistance (Ohm) | <10 ⁶ |
| IFA/BIA certificate (DIN EN 60335-2-69:2015) | M |
| Temperature (dry heat) | |
| Continuous | 120 °C |
| Peaks | 140 °C |
| Chemical resistance | |
| Oil/Water | Good |
| Hydrolysis | Good |
| Acid | Good |
| Alkali | Fair |
| Dust release | Excellent |