



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Cellulose Flame Retardant

Cellulose Flame Retardant

Appearance	Yellow/Brown
Use	Pleatable filter media
Composition	Cellulose fibre filter media
Area weight	128 g/m ²
Air Permeability	520 m ³ /m ² /h at 200 Pa
Surface electrical resistance (DIN 54345)	-
IFA/BIA certificate (DIN EN 60335-2-69:2015)	L
Temperature (dry heat)	
Continuous	50 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising agents	Poor
Organic solvents	Fair
Dust release	Very Good
Supports combustion	Fire class F1 according to DIN 53438